



KEURINGSRAPPORT (3.1) - Chemische samenstelling  
FABRIEKS CONTROLE ATTEST (2.2) - Mechanische eigenschappen/  
INSPECTION CERTIFICATE (3.1) - Chemical analysis  
TEST REPORT (2.2) - Mechanical properties

Datum/Date: 2017-04-14

Certificaat nummer/Cert no:

EC24702412 rev. 0

ESAB ordernummer/Our order: 1617537

Ordernummer/Your order: 20031395332

ESAB referentie/Our ref: Adrienn Mészáros Budapest Kft.

Referentie/Your ref:

Klantnummer/Cust no: NLB00033

Faxnummer/Your fax:

Orderdatum/Your date: 20170411

E-mail adres/Your e-mail:

Faktuuraadres/Invoice address  
ZEVIJ BV LASAULEC HEEREVEEN  
POSTBUS 447  
4900 AK OOSTERHOUT  
Netherlands

Verzendadres certificaten/Cert receiver

Afleveradres/Delivery address  
LASAULEC HEERENVEEN  
Lidnr. 403  
KUPER 4  
8447 GK HEERENVEEN  
Netherlands

LEVERING/DELIVERY

Lotnummer/Lot no:

PVR105478510 Hoeveelheid/Quantity:

1 RL

**PRODUCT/PRODUCT**

Merk/Brand: ESAB  
Omschrijving/Desc: OK Autrod 316LSi 0.8mm 5kg  
Artikelnummer/Item no: 1632084600

**CHEMISCHE SAMENSTELLING/  
CHEMICAL COMPOSITION**

**Actual results: acc to EN 10204 - 3.1**

Wire/strip

Overige/Auxiliary:

|            |        |
|------------|--------|
| C          | 0.01%  |
| Si         | 0.80%  |
| Mn         | 1.6%   |
| P          | 0.020% |
| S          | 0.014% |
| Cr         | 19.0%  |
| Ni         | 12.3%  |
| Mo         | 2.6%   |
| Cu         | 0.10%  |
|            | 0.07%  |
| Ferrite FN | 7      |

**CLASSIFICATIES/CLASSIFICATIONS**

EN ISO 14343-A: G 19 12 3 L Si  
SFA/AWS A5.9: ER316LSi  
Werkstoffnummer: ~1.4430

**MECHANISCHE EIGENSCHAPPEN/MECHANICAL PROPS**

**Typical data: acc to EN 10204 - 2.2**

Norm/Standard:

Overige/Auxiliary:

Toestand/Condition:

**TREKPROEF/TENSILE**

|              |           |              |
|--------------|-----------|--------------|
| <u>Rp0.2</u> | <u>Rm</u> | <u>A4-A5</u> |
| 450 MPa      | 600 MPa   | 35 %         |

**KERFSLAGWAARDE/IMPACT**

|             |        |         |         |
|-------------|--------|---------|---------|
| <u>Temp</u> | -60 °C | -110 °C | -196 °C |
| <u>KV</u>   | 95 J   | 70 J    | 45 J    |

**OPMERKINGEN/COMMENTS**

Typical data Impact (KV at -196 °C) 45 J

Product geleverd volgens een QA systeem welke voldoet aan de ISO 9001 norm.  
Dit certificaat is elektronisch aangemaakt en geldig zonder ondertekening.  
Voor vragen:

**Esab Nederland BV - P.O. Box 2236 , 3800 CE Amersfoort , Nederland**

Product supplied under a QA Programme fulfilling the EN ISO 9001 standard.  
This certificate is produced electronically and is valid without signature.  
Please refer any queries to: (see above)

Validation - Chemical Analysis

Validation - Others

Josef Moravek

Quality Manager

Jay Coubrough

Product Manager